



CRYSTALLOGRAPHIC AND ELECTRICAL STUDY OF INDIUM (In^{3+}) SUBSTITUTED YTTRIUM IRON GARNET

Vidhate R.G.¹, Kavade R.B.², Bhandari J.M.³, Jadhav K.M.⁴

¹Anandrao Dhonde Alias Babaji Mahavidyalaya, Kada, Beed.

²Bhagwan Mahavidyalaya, Ashti, Beed.

³Gandhi college Kada, Beed

⁴Department of physics Dr. Babasaheb Ambedkar Marathwada University, Aurangabad.

Corresponding author email: rgvidhate@rediffmail.com

Abstract: In^{3+} was added in to yttrium iron garnet (YIG).samples, with a nominal composition of $\text{Y}_3\text{In}_x\text{Fe}_{5-x}\text{O}_{12}$ with $x= 0.0, 0.2$ and 0.6 were prepared by a solid-state sintering method. The samples were characterized by X-ray diffraction technique. The X-ray diffraction studies of compositions revealed the formation of single phase cubic structure with lattice constant ranging from 12.37 to 12.44 Å.

The FTIR spectra of typical samples are taken in the range of $500\text{-}4000\text{cm}^{-1}$. IR spectra show typical absorption bands indicating the garnet nature of samples. The D.C. electrical resistivity ρ_{dc} was measured in the temperature range $300\text{-}725$ K.

Keyword: Yttrium iron garnet, indium, structural and electrical study.

INTRODUCTION:

Mixed metal oxides with iron (III) oxides as their main component are known as ferrites. Historically ferrites represent an important category of materials, which are in great demands due to their numerous applications in many fields. The electrical and magnetic properties of ferrites are strongly dependent on their chemical composition and their method of preparation [1, 2]. It is important to optimize the electrical and magnetic properties of ferrites, for desired applications. Due to their interesting properties scientists, researchers and engineers are still interested in designing the various types of ferrites material substituted with different cations with different valencies and prepared by different techniques.

In the various types of ferrites rare earth garnet especially yttrium iron garnet (YIG) is of great importance for scientist and technologist because of their applications in microwave communication devices such as circulators, oscillators, gyrators and phase shifters because of its small ferromagnetic resonance line-width, high electrical resistivity and low dielectric loss in microwave regions in many fields [3]. Yttrium iron garnet (YIG) is microwave ferrite, which in polycrystalline form has specific characteristics. The magnetic and crystallographic properties of the magnetic iron garnet have been studied by many workers [4-7]. Substituted iron garnets have found extensive use in wide band non reciprocal microwave devices [8].

EXPERIMENTAL:



The samples of In^{3+} substituted $\text{Y}_3\text{In}_x\text{Fe}_{5-x}\text{O}_{12}$ garnets with $x = 0.0, 0.2$ and 0.6 were prepared by well known double sintering ceramic method in which a molar ratio of analytical Y_2O_3 , Fe_2O_3 and In_2O_3 (all 99.99% pure AR grade chemicals, Mumbai) were mixed thoroughly in stoichiometric proportions and then ground to very fine powder by using agate mortar for about 3 hr. These mixtures in powder form were pre-sintered in a Indfur Programmable muffle furnace at 1200°C for 24 hr and cooled to room temperature slowly at the rate of $2^\circ\text{C}/\text{min}$. The samples were reground and re-fired at 1350°C for 30 hr and slowly cooled to room temperature at the rate of $2^\circ\text{C}/\text{min}$., and then reground for 1 hr. The fine powdered sample was pelletized under the pressure 5 ton/inch².

The electrical measurements were carried out by means of two probe method. The samples in the form of discs were polished well to have smooth parallel surfaces, and then these surfaces were coated with silver paste as a contact material for the electrical measurements. The temperature was measured by using chromel-alumel thermocouple in contact with the surface of the samples. The d.c. electrical resistivity $\rho_{d.c}$ was measured in the temperature range 300-725 K.

RESULT AND DISCUSSION:

Mixed garnet ferrites system under investigation has been structurally investigated by X-ray diffraction technique. The typical XRD pattern shows the reflections namely (321), (400), (420), (422), (431), (521), (611), (444), (640), (642), (800), (842). No extra peaks other than cubic structure have been observed in the XRD pattern. The Bragg peaks are sharp and intense. The lattice parameters are calculated using XRD data and are given in table-1. It is observed from

table-1 that lattice constant increases with increase in indium content 'x'. The ionic radii of yttrium (0.89\AA) Fe^{3+} is (0.67\AA) and indium (0.81\AA) hence we observe variation in the lattice parameter with indium substitution. The bulk density of all samples was measured using Archimedes principle and values are tabulated in table-1. Bulk density increases with increase in indium content 'x'. Using the values of molecular weight and volume of the sample X-ray density was calculated. The values of X-ray density are also listed in Table-1. X-ray density increase with composition 'x'. The observed variation in X-ray density is attributed to increase in volume of the samples. The crystallographic parameters (lattice constant, X-ray density) are in good agreement with reported values [9]. The most intense peak (420) of XRD pattern was used to evaluate particle size of the samples. The particle size was calculated by using Scherer's formula, the values of particle size for all the composition is listed in Table1.






Fig. 1(a): XRD patterns of $Y_3In_xFe_{5-x}O_{12}$.

($x = 0.0, 0.2$ and 0.6)

Table: 1 Lattice constant (a), X-ray density (d_x), bulk density (d_B) porosity (P) and particle size (t) of $Y_3In_xFe_{5-x}O_{12}$.

x	a (Å)	d_x (gm/cm ³)	d_B (gm/cm ³)	P (%)	t (µm)
0.0	12.370	5.179	4.13	20.25	3.42
0.2	12.401	5.224	4.19	19.97	3.25
0.6	12.443	5.333	4.36	18.24	3.53

IR spectra show typical absorption bands indicating the garnet nature of the samples. The band positions obtained from IR spectra are given in Table-2. The vibrational frequency depends upon the cation mass, cation oxygen bonding force, distance etc. From IR spectra, it is revealed that, a broad band appears at around 611 cm⁻¹, 547 cm⁻¹ and 670 cm⁻¹ assignable to the stretching mode of the tetrahedral in the YIG and this indicates that the crystallization of samples is more complete [10-12]. The values of absorption bands are given in Table 4.3. Our results on IR studies are in good agreement with the literature reports. [13]

Table: 2 Vibrational band frequencies ($\nu_1, \nu_2, \nu_3, \nu_4$) of $Y_3In_xFe_{5-x}O_{12}$, for $x = 0.0, 0.2$ and 0.6 .

x	ν_1 (cm ⁻¹)	ν_2 (cm ⁻¹)	ν_3 (cm ⁻¹)	ν_4 (cm ⁻¹)
0.0	547.1	611.9	670.1	---
0.2	547.1	605.5	861.0	914.0
0.6	469.5	609.7	865.9	914.9




Fig.4 (a): IR spectra of $Y_3In_xFe_{5-x}O_{12}$ of typical sample $x = 0.0$.




Fig.4 (b): IR spectra of $Y_3In_xFe_{5-x}O_{12}$ of typical sample $x = 0.2$.




Fig.4 (c): IR spectra of $Y_3In_xFe_{5-x}O_{12}$ of typical samples $x = 0.6$.

ANALYSIS OF ELECTRICAL RESISTIVITY:

The D. C. electrical resistivity (ρ) measurements for all the samples of $Y_3In_xFe_{5-x}O_{12}$ garnet system were carried out in the temperature range of 300-725 K. Plots of $\log \rho$ Vs $1000/T$ are shown in Fig.5. It is observed from resistivity plots that, D.C.

electrical resistivity decreases with increase in temperature. The plot exhibits a relatively sharp kink, which divides the curve in two parts. The resistivity plots obeys Arrhenius relation given by the equation,

$$\rho = \rho_0 e^{\frac{\Delta E}{KT}} \dots 1$$

Using the above relation and from the resistivity plot, the activation energy for two regions that is ferrimagnetic and paramagnetic was calculated and the values are given in table 3. It is observed from table 3 that, activation energy decreases with increase in In^{3+} ions. The experimental results on D.C. electrical resistivity studies closely matches with those reported in the literature [17].

Table: 3 Activation energy (ΔE) in paramagnetic (E_p) and ferrimagnetic (E_f) region of $Y_3In_xFe_{5-x}O_{12}$.






Fig. 5 : Variation of $\log \rho$ versus $1000/T$ of $Y_3In_xFe_{5-x}O_{12}$. ($x = 0.0, 0.2$ and 0.6).

CONCLUSION:

The garnet system In-YIG was prepared by a solid-state sintering method. The parameter lattice constant increases slightly with In^{3+} substitution. IR spectra show typical absorption bands indicating the garnet nature of the samples. It is observed from

x	E_p (eV)	E_f (eV)	ΔE (eV)
0.0	0.25	0.13	0.12
0.2	0.19	0.10	0.09
0.6	0.05	0.01	0.04

resistivity plots that, D.C. electrical resistivity decreases with increase in temperature and activation energy decreases with increase in In^{3+} ions.

REFERENCES:

[1] Ibetombi Soibam, Sumitra phanjoubam, H. B. Sharma, H N K Sharma and Chandra Prakash. Ind. J. Phys. 83 (3) (2009) 285.
 [2] B. K. Kuanr, P. K. Singh, P. Kisan, N. Kumar, S.L.N. Rao, G.P. Srivastava. J. Appl. Phys. 8 (1986) 63

- [3] Guo Cuijing, Zhang Wei, Ji Rongjin, Zeng Yanwei. *J. Magn. Magn. Mater.* 323 (2011) 611.
- [4] S. Geller and M. A. Gilleo *J. Phys. chem. Solids* 3 (1957) 30.
- [5] M. A. Gilleo and Geller *S. Phys. Rev.* 110, (1958) 73.
- [6] M. A. Gilleo, *J. Phys. Chem. Solids* 13 (1960) 33.
- [7] E. E. Anderson *J. Phys. Soc. Japan Suppl.* 17 (1962) 365.
- [8] B. Lax and K. Button, "Microwave ferrites and ferri-magnetics", McGraw-Hill Book Co. Inc New York (1962).
- [9] J. Richard Cunningham and Elmer E. Anderson, *J. Appl. Phys.* 32, (1961) S388.
- [10] A. M. Hotmeister, K. R. Campbell, *J. Appl. Phys.* 72 (1992) 638.
- [11] M. Ristic, I. Nowik, S. Popovic, I. Felner, S. Music, *J. Mater. Lett.* 57 (2003) 2584.
- [12] Zhongjun Cheng, Hua Yang, Lianxiang Yu, Yuming Cui, Shouhua Feng, *J. Magn. Magn. Mater.* 302 (2006) 259.
- [13] A. Kenneth, Wickersheim, *J. Appl. Phys.* 32 (1961) 205S.
- [14] J. Smit and H. P. J. Wijn, *Ferrites*, New York, Wiley, 1959.
- [15] Hongjie Zhao Ji Zhou Yang Bai Zhilun Gui Longtu Li, *J. Magn. Magn. Mater.* 280 (2004) 208.
- [16] K. Iwachi, *Jap. Appl. Phys.* 10 (1971) 1520.
- [17] I. D. Lomako, V.I. Pavlov, and N.Ya. Shishkin, *Crystallo. Reports*, 48 (2003) 116.